

## Internationale Werkstoffe im Vergleich

*Comparison of international materials*

Correspondance internationale des matières

W.-Nr. Code matériau	DIN	AISI	UNS	SS	AFNOR	BS
1.4005	X 12 CrS 13	416	S 41600	2380	Z 11 CF 13	416 S 21
1.4006	X 10 CrS 13	410	S 41000	2302	Z 10 C 13	410 S 21
1.4016	X 6 CrS 17	430	S 43000	2320	Z 8 C 13	430 S 15
1.4021	X 20 CrS 13	420	S 4200	2303	Z 20 C13	420 S 37
1.4034	X 46 CrS 13			2304	Z 40 C 14	420 S 45
1.4057	X 20 CrNi 17 2	431	S 43100	2321	Z 15 CN 16.02	431 S 29
1.4104	X 12 CrMoS 17	430 F	S 43020	2383	Z 13 CF 17	441 S 29
1.4112	X 90 CrMoV 18	440 B	S 44003			
1.4122	X 35 CrMo 17					
1.4301	X 5 CrNi 18 10	304	S 30400	2332	Z 6 CN 18.09	304 S 15
1.4305	X 10 CrNiS 189	303	S 30300	2346	Z 8 CNF 18.09	303 S 31
1.4306	X 2 CrNi 19 11	304 L	S 30403	2352	Z 2 CN 18.10	304 S 11
1.4310	X 2 CrNi 17 7	301	S 30100	2331	Z 12 CN 18.09	
1.4401	X 5 CrNiMo 17 12 2	316	S 31600	2347	Z 6 CND 17.11	316 S 31
1.4404	X 2 CrNiMo 17 13 2	316 L	S 31603	2348	Z 2 CND 17.12	316 S 11
1.4435	X 2 CrNiMo 18 14 3	316 L	S 31603	2353	Z 3 CN 17.12.03	316 S 11
1.4436	X 5 CrNiMo 17 13 3	316	S 31600	2343	Z 6 CND 18.12.03	316 S 31
1.4438	X 2 CrNiMo 18 16 4	317 L	S 31703	2367	Z 2 CND 19.15.04	317 S 12
1.4439	X 2 CrNiMo 17 13 5	31 LNM				
1.4449	X 5 CrNiMo 17 13	317	S 31700			317 S 16
1.4460	X 4 CrNiMoN 27 5 2	329	S 32900	2324	Z 5 CND 27.50 AZ	
1.4462	X 2 CrNiMoN 22 5 3		S 31803	2377		
1.4539	X 1 CrNiMoCuN 25 20 5		N 08904	2562	Z 1 NCDU 25.20	
1.4541	X 6 CrNiTi 18 10	321	S 32100	2337	Z 6 CNT 18.10	321 S 31
1.4550	X 6 CrNiNb 18 10	347	S 34700	2338	Z 6 CNNb 18.10	347 S 31
1.4571	X 6 CrNiMoTi 17 12 2	316 Ti	S 31635	2350	Z 6 CNDT 17.12	320 S 31
1.4713	X 10 CrAl 7				Z 8 Ca 7	
1.4724	X 10 CrAl 13					
1.4742	X 10 CrAl 18				Z 10 CAS 18	
1.4762	X 10 CrAl 24	446	S 44900	2322	Z 10 CAS 24	
1.4821	X 20 CrNiSi 25 4					
1.4828	X 15 CrNiSi 20 12	309	S 30900		Z 15 CNS 20.12	309 S 24
1.4841	X 15 CrNiSi 25 20	314	S 31400		Z 12 CNS 25.20	
1.4845	X 12 CrNi 25 21	310 S	S 31008	2361	Z 12 CN 25.20	310 S 24
1.4864	X 12 NiCrSi 36 16	330	N 08330		Z 12 CNS 35.16	3076 NA 17
1.4876	X 10 NiCrAlTi 32 20	B 163			Z 8 NC 32.21	3076 NA 15 H
1.4878	X 12 CrNiTi 18 9		S 32100	2337	Z 6 CNT 18.12	321 S 51
2.4068	LC Ni 99	B 160				
2.4360	Ni Cu 30 Fe	B 164				3076 NA 13
2.4375	Ni Cu 30 Al					3076 NA 18
2.4610	Ni Mo 16 Cr 16 Ti					3076 NA 45
2.4816	Ni Cr 15 Fe	B 166				3076 NA 14
2.4856	Ni Cr 21 Mo					3076 NA 43